

PRODUCT DATA

STRATAGRID

StrataGRID® is a geogrid that reinforces soil by interacting with soil particles creating a durable and lasting soil and geosynthetic composite. These high performance geogrids are constructed of high molecular weight and high tenacity polyester yarns that are precision knitted into a dimensionally stable, uniform network of apertures providing superior tensile reinforcement. A proprietary UV stabilized coating provides further chemical and mechanical benefits. StrataGRID is engineered to be mechanically and chemically durable, in both the harsh construction installation phase and in aggressive soil environments (pH range from 2-10).

Design Properties

ULTIMATE AND CREEP LIMITED TENSILE STRENGTHS			Microgrid ^{1,2}	SG150 ¹	SG200	SG350	SG500	SG550	SG600	SG700
Ultimate Strength ^{2,3}	ASTM D 6637 Method A	lbs/ft (kN/m)	2,000 (29.2)	1,875 (27.4)	3,500 (51.1)	4,900 (71.5)	6,400 (93.4)	8,150 (118.9)	9,100 (132.8)	11,700 (170.7)
Creep, Limited Strength	ASTM D 5262	lbs/ft (kN/m)	1,266 (18.5)	1,165 (17.0)	2,215 (32.3)	3,101 (45.3)	4,051 (59.1)	5,158 (75.3)	5,759 (84.1)	7,405 (108.1)

REDUCTION FACTORS FOR INSTALLATION DAMAGE AND DURABILITY

RF _{Inst. Damage} (Sand, Silt & Clay, D ₅₀ < 0.6mm)	1.20	1.05	1.05	1.05	1.05	1.05	1.05	1.05	1.05
RF _{Inst. Damage} (3/4" minus Angular Aggregate, D ₅₀ < 6mm)	1.30	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10
RF _{Inst. Damage} (1.5" minus Angular Aggregate, D ₅₀ < 20mm)	1.40	1.20	1.20	1.20	1.20	1.20	1.20	1.20	1.20
RF _{Durability}	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10	1.10

LONG-TERM DESIGN STRENGTH (LTDS or T_d)⁴

For Sand, Silt & Clay	lbs/ft (kN/m)	959 (14.0)	1,008 (14.7)	1,918 (28.0)	2,685 (39.2)	3,507 (51.2)	4,466 (65.2)	4,987 (72.8)	6,411 (93.6)
For 3/4" minus Angular Aggregate	lbs/ft (kN/m)	885 (12.9)	962 (14.0)	1,831 (26.7)	2,563 (37.4)	3,348 (48.9)	4,263 (62.2)	4,760 (69.5)	6,120 (89.3)
For 1.5" minus Angular Aggregate	lbs/ft (kN/m)	822 (12.0)	882 (12.9)	1,678 (24.5)	2,349 (34.3)	3,069 (44.8)	3,908 (57.0)	4,363 (63.7)	5,610 (81.9)

SOIL INTERACTION COEFFICIENTS FOR PULLOUT (C_i) AND DIRECT SLIDING (C_{ds})

Silts/Clay (ML, CL)	0.6 - 0.7
Sandy Silts & Clay (SC, GC)	0.7 - 0.8
Uniformly-Graded Sands, Silty Sand (SP, SM)	0.8 - 0.9
Gravel, Sand Gravel Mix, Well-Graded Sand (SW, GP, GW)	0.9 - 1.0

MOLECULAR PROPERTIES


Item	Unit	Spec.
Molecular Weight (min.)	g/mol	25,000
Caboxyl End Group (CEG) Count (max.)	meq/kg	30

Physical Properties

Roll Dimensions ^{5,6}	Width x Length	feet (m)	10 x 225 (3.04 x 68.6)	6 x 150 (1.83 x 45.7)	6 x 300 (1.83 x 91.4)	6 x 300 (1.83 x 91.4)	6 x 300 (1.83 x 91.4)	6 x 300 (1.83 x 91.4)	6 x 300 (1.83 x 91.4)	6 x 300 (1.83 x 91.4)
Area	Sq. yds (Sq. m.)		250 (209.0)	100 (83.6)	200 (167.2)	200 (167.2)	200 (167.2)	200 (167.2)	200 (167.2)	200 (167.2)
Weight per Roll	lbs (kg)		105 (47.6)	45 (20.4)	110 (49.9)	130 (59.0)	155 (70.3)	170 (77.1)	180 (81.6)	210 (95.3)

- Denotes both machine and cross-machine direction strength (biaxial strength).
 - MicroGrid ultimate tensile strength determined in accordance with ASTM D 4595.
 - Minimum Average Roll Values for machine direction unless otherwise noted (Lot Average minus 2 x Standard Deviation).
 - LTDS or T_d = T_{ult} / (RF_{creep} x RF_{installation damage} x RF_{durability}).
 - Special order roll sizes are available for SG product styles 12-ft. or 18-ft. widths and/or custom roll lengths.
 - Roll weights are average values including shipping cores. Actual roll weights may vary.
 - StrataGRID soil and segmental retaining wall unit interface properties are available upon request.
 - Note: For Permanent walls the T_d needs to be factored for uncertainties; Typically RF_{uncertainties} = 1.5.
- This product specification supersedes all prior specifications for the products described and is not applicable to any products shipped prior to JANUARY 1, 2008.

12-foot and 18-foot roll widths available upon request



STRATA

380 Dahlonega Road, Suite 200, Cumming, GA 30040, USA
 Email: strata@geogrid.com Website: www.geogrid.com (770) 888-6688 (800) 680-7750 Fax: (770) 888-6680


SGRID_DATA_2007.11

Strata Systems, Inc. has refined the science of soil reinforcement. Our success is a direct result of the power of STRATAGRID® performance and its ability to solve common civil engineering problems. STRATAGRID interacts with the soil particles to create a permanent composite soil/geosynthetic structure. These high performance geogrids are constructed of high tenacity polyester yarn utilizing a complex knitting process to provide superior engineering properties.

Applications

- SEGMENTAL RETAINING WALLS
- REINFORCED STEEP SLOPES
- REINFORCED EMBANKMENTS OVER SOFT SOIL
- LANDSLIDE REPAIR
- REINFORCED FOUNDATIONS

Distributed by:



STRATA

380 Dahlonega Road, Suite 200, Cumming, GA 30040, USA

Email: strata@geogrid.com Website: www.geogrid.com (770) 888-6688 (800) 680-7750 Fax: (770) 888-6680

©2007 by Strata Systems, Inc. The following are trademarks of Strata Systems, Inc.: STRATAGRID, STRATANET, STRATADRAIN. Specifications subject to change without notice. The products are specifically designed for the applications listed herein. The sizing, use and selection of the products should be completed by a competent design professional. The performance data herein reflect Strata Systems, Inc. expectation based on tests conducted in accordance with recognized standard methods. The sale of these products shall be subject to the Terms and Conditions as set forth in Strata Systems, Inc. sales forms. Such Terms and Conditions of Sale will provide that Strata Systems, Inc. will have no liability for consequence damages and will include certain limited express warranties concerning these products. All other express and implied warranties of merchantability and fitness for a particular purpose are disclaimed by Strata Systems, Inc. No agent, employee or representative of Strata Systems, Inc. is authorized to modify this disclaimer. Printed in U.S.A.